

ANCONA



Composition 100% Polyester	Surface 100% Polyester	Base material 100% Polyester
Roll length approx. 30m	Width 142 cm +/- 2 cm	Usable width 140 cm +/- 2 cm
Weight / m2 410 g +/- 5%	Abrasion resistance DIN EN ISO 12947-1+2 > 100.000 T Category A	Pilling DIN EN ISO 12945-2 (2000 T) 4-5 Category A
Tensile strength DIN EN ISO 13934-1 Warp 517 (22,50) Weft 468 (64,50) Category B/B	Tear growth resistance DIN EN ISO 13937-3 N Warp 95,80 Weft 40,40 Category A/A	Resistance to seam slippage DIN EN ISO 13936-2, 180 N Warp 1,0mm Weft 1,0mm Category A/A
Fastness to rubbing dry DIN EN ISO 105-X12 Bright colors 5 Dark colors 4-5 Category A/A	Fastness to rubbing wet DIN EN ISO 105-X12 Bright colors 4-5 Dark colors 4 Category A/A	Fastness to light DIN EN ISO B 02 4-5 Category B

Item specification according to DIN EN 14465: 2006

All results were gathered from differenz samples and represent average indicative values.



REACH
Passed



AZO-Color
(\$35 LMBG B 82.02-2,3,3)
Passed

Cleaning instructions

